

# Vydyne® 21Z-NT01A2

Polyamide 66

Ascend Performance Materials Operations LLC

Message:

Vydyne 21Z-NT01A2 is a neat PA66 resin that is designed for extrusion-compounding applications. This grade is unique in its class with its high concentration of amine end groups that is proven to be an advantage for hydrolysis-sensitive formulations. Resistance of Vydyne 21Z-NT01A2 to heat, oil and wear is typical of PA66 neat resins.

Typical Applications/End Uses:

Compounding

General Information			
Features	Gasoline Resistance		
	General Purpose		
	Good Abrasion Resistance		
	Good Chemical Resistance		
	Good Toughness		
	High Rigidity		
	High Strength		
	Low Viscosity		
	Oil Resistant		
	Solvent Resistant		
Uses	Compounding		
	General Purpose		
Agency Ratings	EC 1935/2004		
	EU 10/2011		
	EU 2023/2006		
	FDA 21 CFR 177.1500		
RoHS Compliance	RoHS Compliant		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Compounding		
	Compounding Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm <sup>3</sup>	ISO 1183
Viscosity Number (H2SO4 (Sulphuric Acid))	137 to 145	cm <sup>3</sup> /g	ISO 307
Bulk Density	674	g/l	ASTM D1895
Moisture Content	0.50	%	ASTM D6869

Relative Viscosity <sup>1</sup>	45.0 to 49.0		ASTM D789
Amino End Groups <sup>2</sup>	78 mmol/kg, min		Internal Method
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	260	°C	ISO 11357-3
Optical	Nominal Value	Unit	Test Method
Yellowness Index	4.0	YI	ASTM D1925
NOTE			
1.	Formic acid		
2.	STM-00344 (APM internal test protocol)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT