

SumiDurez PM 8375

Phenolic

SumiDurez Singapore Pte Ltd

Message:

PM 8375 Phenolic is a two-stage special purpose molding compound. It is especially designed for applications requiring high solder resistance. Typical applications include coil bobbins and switches.
JIS Type EG

General Information			
Features	Flame Retardant		
	General Purpose		
Uses	Bobbins		
	Electrical Parts		
	General Purpose		
	Switches		
Appearance	Black		
Forms	Granules		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.47	g/cm ³	JIS K6911
Apparent Density	0.62	g/cm ³	JIS K6911
Molding Shrinkage - Flow (Transfer Molded)	0.60	%	JIS K6911
Water Absorption (24 hr)	0.30	%	JIS K6911
Mechanical	Nominal Value	Unit	Test Method
Flexural Strength	85.0	MPa	JIS K6911
Compressive Strength	200	MPa	JIS K6911
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	2.7	kJ/m ²	JIS K6911
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	180	°C	JIS K6911
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength ¹	11	kV/mm	JIS K6911
Insulation Resistance			JIS K6911
-- ²	1.0E+11	ohms	
-- ³	1.0E+8	ohms	
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.490 mm)	V-0		UL 94

NOTE	
1.	60 V/sec
2.	Before Boiling
3.	After Boiling

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT