

# LGH 305

High Impact Polystyrene

LG Polymers India Pvt. Ltd.

## Message:

LGSTRENE LGH 305 is a High Impact Polystyrene material. It is available in Asia Pacific. Primary attribute of LGSTRENE LGH 305: Flame Rated.

General Information			
Features	Good Flow		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	5.5	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.40 to 0.80	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	93		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	23.5	MPa	ASTM D638
Tensile Elongation (Break)	50	%	ASTM D638
Flexural Modulus	1960	MPa	ASTM D790
Flexural Strength	37.3	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (6.35 mm)	74	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	80.0	°C	ASTM D648
Vicat Softening Temperature	98.0	°C	ASTM D1525
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT