

VITAMIDE® TS30GY6278

Polyamide 66/6 Copolymer

Jackdaw Polymers

Message:

VITAMIDE® TS30GY6278 is a Polyamide 66/6 Copolymer (Nylon 66/6) product. It is available in Europe.

Characteristics include:

- Flame Rated
- Heat Stabilizer
- Impact Modified

General Information			
Additive	Heat Stabilizer		
	Impact Modifier		
Features	Heat Stabilized		
	Impact Modified		
Appearance	Grey		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm ³	ASTM D792, ISO 1183
Water Absorption (23°C, 24 hr)	1.3	%	ASTM D570, ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	85.0	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	30	%	ASTM D638, ISO 527-2
Flexural Modulus	2500	MPa	ASTM D790, ISO 178
Flexural Stress			
--	100	MPa	ISO 178
Break	100	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	6.5	kJ/m ²	ISO 179
Charpy Notched Impact Strength ¹	6.50	kJ/m ²	ASTM D256
Charpy Unnotched Impact Strength ²	No Break		ASTM D256
Charpy Unnotched Impact Strength	No Break		ISO 179
Notched Izod Impact Strength	6.5	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	205	°C	ASTM D648, ISO 75-2/B
1.8 MPa, Unannealed	90.0	°C	ASTM D648, ISO 75-2/A
Melting Temperature	240	°C	ASTM D2117, ISO 1218
CLTE - Flow	7.0E-5	cm/cm/°C	ASTM D696

Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257, IEC 60093
Dielectric Strength	26	kV/mm	ASTM D149, IEC 60243-1
Comparative Tracking Index			
Solution A	600	V	IEC 60112
-- ³	600	V	ASTM D3638
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Oxygen Index	24	%	ASTM D2863, ISO 4589-2
NOTE			
1.	Method B		
2.	Method A		
3.	Solution A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

