

NOVALENE 7300P

Thermoplastic

NOVA Polymers, Inc.

Message:

NOVALENE is a reliable, economical impact modifier, ideal for use by molders and compounds of polypropylene and polyethylene.

General Information			
Appearance	Natural color		
Forms	Particle		
Processing Method	Blow molding		
	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.915	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	0.60	g/10 min	ASTM D1238
Mooney Viscosity	60	MU	ASTM D1646
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	78		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-40.0	°C	ASTM D746
Additional Information			
Moisture Content, ASTM D 4019-88: 0.19 %Product Base, EPDM: 60 %Product Base, HDPE: 40 %			
Injection	Nominal Value	Unit	
Processing (Melt) Temp	199	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT