

SLOVAMID® 66 BT LS

Polyamide 66

Plastcom

Message:

Modified for general use, with excellent manufacturing properties, characterized by high strength and toughness also at minus temperatures. UV stabile. Used in automotive, electrical, engineering and consumer goods industry. Application: electric tools, gear wheels, clamps, fasteners, toolbodies, webbing slings for cable harnesses.

General Information			
Additive	UV Stabilizer		
Features	Good Processability		
	Good UV Resistance		
	High Strength		
	Low Temperature Toughness		
	Ultra High Toughness		
Uses	Automotive Applications		
	Electrical/Electronic Applications		
	Engineering Parts		
	Fasteners		
	Gears		
	Power/Other Tools		
Appearance	Colors Available		
	Natural Color		
Processing Method	Injection Molding		
Resin ID (ISO 1043)	PA 66		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (275°C/0.325 kg)	4.0	g/10 min	ISO 1133
Molding Shrinkage			STM 64 0808
Across Flow	1.9	%	
Flow	1.8	%	
Water Content	0.20	%	ISO 960
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3200	MPa	ISO 527-2
Tensile Stress (Yield)	80.0	MPa	ISO 527-2
Tensile Strain (Yield)	3.0	%	ISO 527-2
Flexural Modulus	2700	MPa	ISO 178

Flexural Stress	110	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-20°C	1.5	kJ/m ²	
23°C	2.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179
-20°C	90	kJ/m ²	
23°C	100	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	68.0	°C	ISO 75-2/B
Vicat Softening Temperature	250	°C	ISO 306/B
Melting Temperature (DSC)	260	°C	ISO 3146
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+14	ohms·cm	IEC 60093
Electric Strength	30	kV/mm	IEC 60243-1
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-2		UL 94
Glow Wire Ignition Temperature	960	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	280 to 300	°C	
Mold Temperature	80.0 to 90.0	°C	
Injection Pressure	70.0 to 120	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

