

Stanyl® ForTii™ LED LX

Polyamide 4T
DSM Engineering Plastics

Message:

Stanyl® ForTii™ LED LX is a Polyamide 4T (Nylon 4T) material filled with glass fiber. It is available in Asia Pacific, Europe, or North America. Primary attribute of Stanyl® ForTii™ LED LX: Flame Rated.

General Information			
UL YellowCard	E172082-101227203		
Filler / Reinforcement	Glass Fiber		
Physical	Nominal Value	Unit	Test Method
Density	1.77	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	0.80	%	
Flow	0.60	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	0.40	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	10000	MPa	ISO 527-2
Tensile Stress (Break)	100	MPa	ISO 527-2
Tensile Strain (Break)	1.2	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	1.5	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	230	°C	ISO 75-2/A
Melting Temperature ¹	325	°C	ISO 11357-3
Flammability	Nominal Value		Test Method
Flammability Classification			IEC 60695-11-10, -20
0.750 mm	HB		
1.50 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature	100	°C	
Drying Time	4.0 to 8.0	hr	
Rear Temperature	320 to 330	°C	
Middle Temperature	325 to 335	°C	
Front Temperature	330 to 335	°C	
Nozzle Temperature	330 to 335	°C	
Processing (Melt) Temp	330 to 340	°C	
Mold Temperature	100 to 150	°C	
Injection Rate	Moderate-Fast		

Back Pressure	0.500 to 3.00	MPa
Screw Compression Ratio	2.5:1.0	
NOTE		
1.	10°C/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

