

# AXLENE® 35RM

Polypropylene Random Copolymer

INDELPRO, S.A. de C.V.

## Message:

AXLENE35RM is a clarified random copolymer that is designed for screw-injection molding. The base resin in this product meets the requirements of the FDA contained in the Code of Federal Regulations in 21 CFR 177.1520.

Features:

Good clarity

Good processing stability

Good dimensional stability

Typical Applications:

Containers

Houseware

Thin-wall injection molding

General Information			
Additive	Clarifier		
Features	Good Clarity		
	Good dimensional stability		
	Good processing stability		
	Random copolymer		
Uses	Thin wall parts		
	Household goods		
	Container		
Agency Ratings	FDA 21 CFR 177.1520		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm <sup>3</sup>	ASTM D792A
Melt Mass-Flow Rate (MFR)	35	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	27.0	MPa	ASTM D638
Tensile Elongation (Yield)	12	%	ASTM D638
Flexural Modulus	950	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	35	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	87.0	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT