

Durethan® DP AKV 30 HR EF 901510

Polyamide 66

LANXESS Asia/Pacific

Message:

PA 66, 30 % glass fibers, injection molding, improved flowability, heat-aging stabilized, hydrolysis stabilized

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 30% filler by weight		
Additive		Hydrolysis resistance heat stabilizer		
Features		Good liquidity Hydrolysis resistance Thermal Stability		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.32	--	g/cm ³	ISO 1183
Apparent Density	0.70	--	g/cm ³	ISO 60
Molding Shrinkage				ISO 2577
Vertical flow direction: 290°C, 2.00mm ¹	0.82	--	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 2.00mm ²	0.040	--	%	ISO 2577
Flow direction: 290°C, 2.00mm ³	0.37	--	%	ISO 2577
Flow direction: 120°C, 4 hours, 2.00mm ⁴	0.060	--	%	ISO 2577
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	8200	5000	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	150	100	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.6	8.0	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	8100	5000	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% strain, 23°C	225	125	MPa	ISO 178/A
23°C ⁶	240	150	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	4.0	6.0	%	ISO 178/A
Burning Behavior ⁸	passed	--		ISO 3795
ISO Shortname	PA 66, GHRW, 14-080, GF30	--		ISO 1874
Residual Moisture Content	0.030 - 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method

Charpy Notched Impact Strength				ISO 179/1eA
-30°C	< 10	--	kJ/m ²	ISO 179/1eA
23°C	10	--	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	70	--	kJ/m ²	ISO 179/1eU
23°C	80	80	kJ/m ²	ISO 179/1eU
Notched Izod Impact				ISO 180/1A
-30°C	< 10	< 10	kJ/m ²	ISO 180/1A
23°C	10	15	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	65	60	kJ/m ²	ISO 180/1U
23°C	70	70	kJ/m ²	ISO 180/1U
Multi-Axial Instrumented Impact Energy				ISO 6603-2
-30°C	2.50	--	J	ISO 6603-2
23°C	2.70	--	J	ISO 6603-2
Multi-Axial Instrumented Impact Peak Force				ISO 6603-2
-30°C	756	--	N	ISO 6603-2
23°C	774	--	N	ISO 6603-2
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	250	--	°C	ISO 75-2/B
1.8 MPa, not annealed	240	--	°C	ISO 75-2/A
Melting Temperature ⁹	263	--	°C	ISO 11357-3
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 - 6.0		hr	
Processing (Melt) Temp	280 - 300		°C	
Mold Temperature	80.0 - 120		°C	
NOTE				
1.	60x60x2mm, 80°C MT, 600 bar			
2.	60x60x2mm			
3.	60x60x2mm, 80°C MT, 600 bar			
4.	60x60x2mm			
5.	2.0 mm/min			
6.	2.0 mm/min			
7.	2 mm/min			

8.	US-FMVSS302
9.	10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

