

Weifang Kingdom CPET101

Chlorinated Polyethylene

Weifang Kingdom Plastic Co., Ltd

Message:

FEATURES: It is equivalent to Dow's TYRIN 6000

| General Information | | | |
|------------------------------|-----------------------------|-------|-----------------|
| Features | Flame Retardant | | |
| | Good Chemical Resistance | | |
| | Good Flexibility | | |
| | Good Processability | | |
| | Good Weather Resistance | | |
| | High Heat Resistance | | |
| | High Molecular Weight | | |
| | Low Temperature Flexibility | | |
| | Low Temperature Resistant | | |
| | Low to No Taste | | |
| Uses | Film | | |
| | Fittings | | |
| | Piping | | |
| | Plastics Modification | | |
| | Profiles | | |
| | Sheet | | |
| | Wire & Cable Applications | | |
| Appearance | White | | |
| Forms | Powder | | |
| Physical | Nominal Value | Unit | Test Method |
| Chlorine Content | 34.0 to 36.0 | wt% | ISO 1158 |
| Ash Content | < 2.0 | % | ISO 247 |
| Average Particle Size | 300 | µm | ISO 2591-1 |
| Heat of Fusion | < 2.00 | J/g | Internal Method |
| Melt Viscosity | 2400000 | mPa·s | ISO 11443 |
| Volatiles | < 0.30 | % | ISO 248 |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Stress (100% Strain) | 1.00 | MPa | ISO 37 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT