

# Interpol 47-5124/47-5205

Polyurethane (Polyester based)  
Cook Composites and Polymers

Message:

Interpol 47-5124/47-5205 is a Polyurethane (Polyester based) (PUR-Ester) product. It can be processed by casting or injection molding and is available in North America.  
Characteristics include:  
Good Flexibility  
Good Toughness

General Information			
Features	Good Flexibility		
	Good Toughness		
Forms	Pellets		
Processing Method	Casting		
	Injection Molding		
Hardness	Nominal Value		Test Method
Durometer Hardness (Shore D)	78		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1370	MPa	ASTM D638
Tensile Strength (Yield)	39.3	MPa	ASTM D638
Tensile Elongation (Yield)	27	%	ASTM D638
Flexural Modulus	2590	MPa	ASTM D790
Flexural Strength (Yield)	95.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	96	J/m	ASTM D256
Unnotched Izod Impact	750	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	52.8	°C	ASTM D648
Thermoset	Nominal Value	Unit	
Thermoset Components			
Hardener	Mix Ratio by Weight: 27		
Resin	Mix Ratio by Weight: 100		
Demold Time (100°C)	960	min	
Injection	Nominal Value	Unit	
Mold Temperature	54.4 to 65.6	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT