

Sumiflex® K K58DL13

Polyvinyl Chloride Elastomer
Mitsubishi Chemical Corporation

Message:

Sumiflex® K K58DL13 is a Polyvinyl Chloride Elastomer (PVC Elastomer) material. It is available in Asia Pacific for injection molding. Primary attribute of Sumiflex® K K58DL13: Low Gloss.
Typical application of Sumiflex® K K58DL13: Automotive

General Information			
Features	Low Gloss		
Uses	Automotive Applications		
	Automotive Interior Parts		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.21	g/cm ³	JIS K7112
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (10 sec)	49		JIS K6253
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	2.70	MPa	JIS K6723
Tensile Stress (Break)	5.10	MPa	JIS K6723
Tensile Elongation (Break)	250	%	JIS K6723

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT