# Braskem PE SHC7260

### High Density Polyethylene

#### Braskem

#### Message:

Description:

SHC7260 is a high-density polyethylene, developed for the injection molding which presents high hardness and stiffness, besides low tendency to warpage.

The minimum biobased content of this grade is 94%, determined according to ASTM D6866.

Application:

Boxes for frozen food and agricultural products, industrial containers and boxes for general use, Safety Helmets, Toilet seats, Housewares, Toys, Lids, Caps &Closures, Pallets and Boxes for beverages bottles.

General Information			
Features	Low warpage		
	Rigidity, high		
	Updatable resources		
	Compliance of Food Exposure		
	High hardness		
Uses	Pallets		
	Non-specific food applications		
	Cover		
	Shield		
	Household goods		
	Bottle		
	General		
	Shell		
	Toys		
Agency Ratings	FDA 21 CFR 177.1520		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.959	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	7.2	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (50°C, 2.00 mm, 100% Igepal, F50)	< 4.00	hr	ASTM D1693
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, Compression Molded)	64		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, Compression Molded)	30.0	MPa	ASTM D638

Tensile Elongation (Yield, Compression Molded)	7.5	%	ASTM D638
Flexural Modulus - 1% Secant			
(Compression Molded)	1350	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Compression			
Molded)	35	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45			
MPa, Unannealed, Compression Molded)	76.0	°C	ASTM D648
Vicat Softening Temperature	126	°C	ASTM D1525 <sup>1</sup>
Additional Information	Nominal Value	Unit	Test Method
Biobased Content	> 94	%	ASTM D6866
NOTE			
1.	压 力1 (10N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

