

Unigel PS U285

General Purpose Polystyrene

Unigel Plásticos

Message:

High gloss and transparency.
Dimensional stability and high heat resistance.
Recommended for foam process and in blends with high impact polystyrene.
Approved for food contact

General Information			
Features	Food Contact Acceptable		
	Good Dimensional Stability		
	High Clarity		
	High Gloss		
	High Heat Resistance		
Uses	Blending		
	Foam		
Agency Ratings	FDA 21 CFR 177.1640		
Appearance	Clear/Transparent		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	1.9	g/10 min	ASTM D1238
Water Absorption (Equilibrium)	0.030	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3250	MPa	ASTM D638
Tensile Strength (Break)	52.0	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.50 mm)	19	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.30 mm)	91.0	°C	ASTM D648
Vicat Softening Temperature	105	°C	ASTM D1525 ¹
Flammability	Nominal Value	Test Method	
Flame Rating	HB	UL 94	
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

