

Clyrell RC215M

Polypropylene Random Copolymer

LyondellBasell Industries

Message:

"Clyrell" RC215M is a alpha olefin modified polypropylene random copolymer especially designed for cast film technology. It offers an excellent clarity and gloss, a very low haze, a wide hot tack range and a low seal-initiation temperature of 120°C. It is designed for quality packaging applications, either as monolayer film or as welding layer in coextruded structures. "Clyrell" RC215M is easy processable on commercial cast film equipment. It contains slip and antiblock additives.

"Clyrell" RC215M is suitable for food contact.

General Information			
Additive	Antiblock		
	Slip		
Features	Antiblocking		
	Food Contact Acceptable		
	High Clarity		
	High Gloss		
	Low Temperature Heat Sealability		
	Random Copolymer		
	Slip		
Uses	Cast Film		
	Film		
	Packaging		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	66		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1050	MPa	ISO 527-2/1
Tensile Stress (Yield)	27.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield	10	%	
Break	600	%	
Coefficient of Friction			ASTM D1894
vs. Itself - Dynamic, Cast Film	0.50		
vs. Itself - Static, Cast Film	0.50		

Films	Nominal Value	Unit	Test Method
Secant Modulus - MD ¹ (50 μm, Cast Film)	660	MPa	ASTM D882
Tensile Strength - MD ²			ASTM D882
Yield, 50 μm, Cast Film	22.0	MPa	
Break, 50 μm, Cast Film	35.0	MPa	
Tensile Elongation - MD ³ (Break, 50 μm, Cast Film)	750	%	ASTM D882
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	1.5	kJ/m ²	
23°C	3.4	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	65.0	°C	ISO 75-2/B
Vicat Softening Temperature	130	°C	ISO 306/A50
Optical	Nominal Value	Unit	Test Method
Gloss (50.0 μm, Cast Film)	90		ASTM D2457
Haze (50.0 μm, Cast Film)	< 1.0	%	ASTM D1003
NOTE			
1.	25 mm/min		
2.	500 mm/min		
3.	500 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

