

# STABAMID® 26 JE 1

Polyamide 66

Solvay Polyamide & Intermediates

Message:

STABAMID® 26 JE 1 is a Polyamide 66 (Nylon 66) material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.  
Primary attribute of STABAMID® 26 JE 1: Heat Stabilizer.  
Typical applications include:  
Fabrics/Fibers  
Yarn

General Information		
Additive	Heat Stabilizer	
Features	Heat Stabilized	
Uses	Fibers	
	Yarn	
Forms	Pellets	
Physical	Nominal Value	Unit
Density	1.14	g/cm <sup>3</sup>
Apparent Density	0.70	g/cm <sup>3</sup>
Humidity - at Packaging	< 0.35	%
Relative Viscosity		
Formic Acid 90%	46.2	
Sulfuric Acid 96%	2.62	
Viscosity		
Formic Acid 90%	132	cm <sup>3</sup> /g
Sulfuric Acid 96%	143	cm <sup>3</sup> /g
Amino End Groups	54	meq/kg
Granulometry <sup>1</sup>	2.50	
Thermal	Nominal Value	Unit
Melting Temperature <sup>2</sup>	260	°C
Peak Crystallization Temperature (DSC)	220	°C
NOTE		
1.	g/100 chips	
2.	2nd melting	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: [sales@su-jiao.com](mailto:sales@su-jiao.com)

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

