

Sylvin 2900-75 Brown 7407

Polyvinyl Chloride
Sylvin Technologies Incorporated

Message:
Sylvin 2900-75 Brown 7407 Is A Vinyl Compound Formulated With FDA Sanctioned Ingredients For Extrusion Or Injection Molding Applications.

General Information			
Agency Ratings	FDA not rated		
Appearance	Brown		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw A	75		ASTM D2240
Shaw A, 10 seconds	75		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	15.2	MPa	ASTM D638
Tensile Elongation (Break)	430	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tear Strength	52.5	kN/m	ASTM D624
Thermal	Nominal Value	Unit	
Melting Temperature	163 - 174	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China


WECHAT