

DynaChar™ C134

Polyolefin

Polymer Dynamix

Message:

Non Halogen Flame Retardant TPO - HFFR - LSZH

Features

Excellent Chemical Resistance

Low Temperature Properties

Ultra Low Smoke and Toxicity FR Properties

VW1

Easy extrusion for insulation or jacket

Applications:

Wire and Cable

Industrial

Aerospace

General Information			
Features	Flame Retardant		
	Good Chemical Resistance		
	Halogen Free		
	Low Smoke Emission		
	Low Temperature Resistant		
	Low Toxicity		
Uses	Aerospace Applications		
	Industrial Applications		
	Insulation		
	LSZH Insulation		
	Wire & Cable Applications		
Wire Types	VW-1		
Processing Method	Wire & Cable Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.32	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.50	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	95		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	159	MPa	ASTM D790
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	12.1	MPa	ASTM D412
Tensile Elongation (Break)	> 150	%	ASTM D412
Thermal	Nominal Value	Unit	Test Method

Melting Temperature	160	°C	DSC
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	41	%	ASTM D2863

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

