Geon™ BIO RA7000

Flexible Polyvinyl Chloride PolyOne Corporation

Message:

A flexible vinyl formulated to achieve a minimum level of 25% bio-based content and classified as a PolyOne Sustainable Solution

| General Information | | | |
|---|----------------------------|-------|-------------|
| Features | Non-Phthalate Plasticizer | | |
| | Renewable Resource Content | | |
| Uses | Building Materials | | |
| | Consumer Applications | | |
| | Industrial Applications | | |
| Forms | Pellets | | |
| Processing Method | Extrusion | | |
| | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.17 | g/cm³ | ASTM D792 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness | | | ASTM D2240 |
| Shore A | 68 | | |
| Shore A, 15 sec | 61 | | |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength ¹ | | | ASTM D638 |
| Break | 11.7 | MPa | |
| 100% Strain | 4.48 | MPa | |
| Tensile Elongation ² (Break) | 420 | % | ASTM D638 |
| Thermal | Nominal Value | Unit | Test Method |
| Brittleness Temperature | -37.8 | °C | ASTM D746 |
| Flammability | Nominal Value | Unit | Test Method |
| Oxygen Index | 21 | % | ASTM D2863 |
| Injection | Nominal Value | Unit | |
| Processing (Melt) Temp | 188 to 199 | °C | |
| Extrusion | Nominal Value | Unit | |
| Melt Temperature | 171 to 182 | °C | |
| NOTE | | | |
| 1. | 510 mm/min | | |
| 2. | 510 mm/min | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

