# Akestra<sup>™</sup> 100

#### Copolyester

### Perstorp Holding AB

#### Message:

Description Akestra<sup>™</sup> 100 is an amorphous thermoplastic copolyester with excellent appearance and clarity. Excellent hydrolytic stability, heat resistance and high strength. Applications Extrusion and injection moulded articles. Blow moulding. Films and sheets.

General Information					
Features	Amorphous				
	High Clarity				
	High Heat Resistance				
	High Strength				
	Hydrolytically Stable				
	Pleasing Surface Appearance				
Uses	Blow Molding Applications				
	Film				
	Sheet				
Forms	Pellets				
Processing Method	Blow Molding				
	Extrusion				
	Film Extrusion				
	Injection Molding				
	Sheet Extrusion				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.27	g/cm³	ASTM D792		
Machanical	Nominal Value	Linit	Tost Mothod		

Specific Gravity	1.27	g/cm³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Elongation (Break)	200	%	ASTM D638
Flexural Modulus	2500	MPa	ASTM D790
Flexural Strength (Yield)	90.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	25	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	100	°C	ASTM D7426
Optical	Nominal Value	Unit	Test Method

Transmittance	91.0	%	ASTM D1003
Haze	1.0	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

