

Viton® GLT-200S

Fluoroelastomer

DuPont Performance Elastomers

Message:

Low temperature peroxide curable FKM gums
25 Mooney. Best low temperature flexibility and sealing.

General Information	
Features	Flexibility at low temperatures
	Solvent resistance
Uses	Washer
	Pipe
	Pipe fittings
	Metal bonding
	Seals
	Coating application
Forms	Particle
Processing Method	Extrusion
	Resin transfer molding
	Coating
	Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.78	g/cm ³	ASTM D792
Mooney Viscosity	25	MU	ASTM D1646
Elastomers	Nominal Value	Unit	Test Method
Compression Set (200°C, 70 hr)	25	%	ASTM D395

Additional Information
Nominal Viscosity, ML 1 + 10, 121°C: 25Polymer Fluorine Content: 64%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

