

# Andur 7500 DP/Curene® 442

Polyurethane (Polyether, TDI)  
Anderson Development Company

Message:

Andur 7500-DP is a polyether (PPG) based liquid, toluene diisocyanate terminated prepolymer. An elastomer with a hardness of 72 to 75 Shore D is obtained when this prepolymer is cured with Curene 442 [4,4'-methylene-bis (orthochloroaniline)]. Elastomers of lower hardness can be obtained by reaction with various polyols and their combination with Curene 442 and other diamines, or through the use of plasticizers.

General Information			
Forms	Liquid		
Physical	Nominal Value	Unit	Test Method
Density	1.18	g/cm³	ASTM D1505
Molding Shrinkage - Flow	1.2	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	75		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% strain	31.0	MPa	ASTM D412
300% strain	38.6	MPa	ASTM D412
Tensile Strength (Yield)	38.6	MPa	ASTM D412
Tensile Elongation (Break)	200	%	ASTM D412
Compression Set	45	%	ASTM D395B
Bayshore Resilience	50	%	ASTM D2632
Thermoset	Nominal Value	Unit	
Pot Life	3.0 - 3.5	min	
Demold Time (100°C)	20	min	
Post Cure Time (100°C)	16	hr	

Additional Information			
Durometer Hardness, ASTM D2240, Shore D: 72 to 77Die C Tear, ASTM D1004: 800 pliAverage Split Tear, ASTM D1938: 280 pliStoichiometry Curative Level: 95%Mix Temperature: Andur 7500 DP: 160-180°F Curene 442: 230-240°F			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT