

Elastamax™ XL 0131-59(50/50)

Styrene Butadiene Block Copolymer

PolyOne Corporation

Message:

Elastamax™XL 0131-59(50/50) is a styrene-butadiene copolymer (SBC) product. It can be processed by injection molding and is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. Elastamax™XL 0131-59(50/50) applications include consumer goods and food contact applications. The main characteristics are: accessible food.

General Information			
Features	Compliance of Food Exposure		
	General		
Uses	General		
	Consumer goods application field		
Agency Ratings	FDA Food Exposure, Not Rated		
Appearance	Opacity		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.958	g/cm ³	ASTM D792
Molding Shrinkage - Flow	1.5	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 10 sec)	48		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Break)	22.3	MPa	ASTM D412A
Tensile Elongation ² (Break)	400	%	ASTM D412A
Additional Information			
配制用于食品接触应用的一种热塑性弹性体化合物.以上列出的物理属性为实验室配制样品,并根据接受试验方法测试获取的典型值.本化合物配方中所用的全部成分均在美国食品及药物管理局《联邦法规法典》第21章“用于包装食品”中列出.该清单涵盖根据应用场合可能适用的许多用途和限制.请联系我们,检查特定产品在特定应用场合的适用性.本说明仅为食品及药物管理局清单关于本产品部分的概述.由用户负责确保此化合物适用于其预期应用.			
NOTE			
1.	510 mm/min		
2.	510 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

