

Syncure™ S1060A Natural

Crosslinked Polyethylene

PolyOne Corporation

Message:

Moisture cross-linked polyethylene composite material. Base resin composition, used in the Syncure system of Plivan.

General Information			
Uses	Wire and cable applications		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Density	0.924	g/cm ³	ASTM D1505
Apparent Density ¹	0.50	g/cm ³	Internal method
Melt Mass-Flow Rate (MFR) ² (190°C/2.16 kg)	0.73	g/10 min	ASTM D1238
Gel Content ³	75	%	ASTM D2765
Deformation ⁴ (131°C)	5.7	%	UL 1581
Thermal creep elongation ⁵	45	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ⁶	11.0	MPa	ASTM D638
Tensile Strength ⁷ (Break)	16.5	MPa	ASTM D638
Tensile Elongation ⁸ (Break)	600	%	ASTM D638
Additional Information			

张力,伸长率,变形值,热蠕变和凝胶值基于95 phr S1060A / 5 phr S1000B系统测量得出;并在90摄氏度的水中硫化6小时.颗粒外观为 1/8"圆柱状.

NOTE	
1.	Geon® 1169
2.	Procedure A
3.	Cross-linked PE, Method B (Non-Arbitration Test)
4.	500g,1 hour
5.	SYV-40
6.	Type 4, 510mm/min
7.	Type 4, 510mm/min
8.	Type 4, 510mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

