Jamplast JPCPE36

Chlorinated Polyethylene

Jamplast, Inc.

Message:

Jamplast JPCPE36 is a Chlorinated Polyethylene material. It is available in North America. Primary attribute of Jamplast JPCPE36: Impact Modified.

| One and I of a marks | | | |
|------------------------------|-----------------|-------|-------------|
| General Information | | | |
| Additive | Impact Modifier | | |
| Features | Impact Modified | | |
| Forms | Pellets | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.16 | g/cm³ | ASTM D792 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A) | 70 | | ASTM D2240 |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Stress (100% Strain) | 1.72 | MPa | ASTM D412 |
| Tensile Strength (Yield) | 9.65 | MPa | ASTM D412 |
| Tensile Elongation (Break) | 700 | % | ASTM D412 |
| Thermal | Nominal Value | Unit | Test Method |
| Brittleness Temperature | -48.3 | °C | ASTM D746 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

