## INEOS HDPE T50-2000-119

High Density Polyethylene Copolymer INEOS Olefins & Polymers USA

## Message:

T50-2000-119 is a high density, narrow molecular weight distribution polyethylene copolymer intended for applications requiring a glossy surface finish and reasonably good impact strength and rigidity. It is characterized by a high melt index which allows easy processing of medium to thin-walled articles. This material meets the Food and Drug Administration requirements of 21 CFR 177.1520.

General Information				
Features	Copolymer			
	Food Contact Acceptable			
	Good Impact Resistance			
	Good Processability			
	High Density			
	High Gloss			
	Medium Rigidity			
	Narrow Molecular Weight Distribution			
Agency Ratings	EC 1907/2006 (REACH)			
	FDA 21 CFR 177.1520			
Forms	Pellets			
Physical	Nominal Value	Unit	Test Method	
Density	0.953	g/cm³	ASTM D4883	
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	20	g/10 min	ASTM D1238	
Environmental Stress-Cracking Resistance (100% Igepal, F50)	1.80	hr	ASTM D1693B	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore D)	66		ASTM D2240	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength <sup>1</sup>			ASTM D638	
Yield	27.6	MPa		
Break	26.8	MPa		
Tensile Elongation <sup>2</sup>			ASTM D638	
Yield	9.1	%		
Break	230	%		
Flexural Modulus - Tangent	1230	MPa	ASTM D790A	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact	28	J/m	ASTM D256	
Notched Izod Impact (Area)	2.77	kJ/m²	ASTM D256	

Thermal	Nominal Value	Unit	Test Method	
Deflection Temperature Under Load (0.45				
MPa, Unannealed)	72.2	°C	ASTM D648	
Brittleness Temperature	< -70.0	°C	ASTM D746	
Vicat Softening Temperature	125	°C	ASTM D1525	
NOTE				
1.	51 mm/min			
2.	51 mm/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



Page 2