

Desmopan® DP 85786A

Thermoplastic Polyurethane Elastomer

Covestro - PUR

Message:

Grade for calendering; no yellowing under the action of UV light; good low-temperature flexibility; high rebound resilience; improved microbial resistance; Improved hydrolysis resistance; Application; Textile coating

General Information			
Features	Good UV Resistance		
	Hydrolysis Resistant		
	Low Temperature Flexibility		
	Microbe Resistant		
	Resilient		
Uses	Fabric Coatings		
RoHS Compliance	RoHS Compliant		
Processing Method	Calendering		
	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A, 23°C)	86		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress ¹			DIN 53504
Break, 23.0 mm	33.0	MPa	
100% Strain, 23°C	7.00	MPa	
300% Strain, 23°C	10.0	MPa	
Tensile Strain ² (Break)	720	%	DIN 53504
Abrasion Resistance (23°C)	31.0	mm ³	ISO 4649-A
Tensile Storage Modulus			ISO 6721-1,-4
-20°C	260	MPa	
20°C	65.0	MPa	
60°C	50.0	MPa	
Impact Resilience (23°C)	64	%	ISO 4662
Elastomers	Nominal Value	Unit	Test Method
Tear Strength ³ (23°C)	74	kN/m	ISO 34-1
Compression Set			ISO 815
23°C, 72 hr	18	%	

70°C, 24 hr	44	%
Injection	Nominal Value	Unit
Drying Temperature	< 80.0	°C
Processing (Melt) Temp	170 to 190	°C
Mold Temperature	20.0	°C
Extrusion	Nominal Value	Unit
Drying Temperature	< 80.0	°C
Melt Temperature	170 to 190	°C
NOTE		
1.	200 mm/min	
2.	200 mm/min	
3.	500 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

