

Tenogel® ABS A3 FR PRTA011 AB341

Acrylonitrile Butadiene Styrene
Petropol Industry and Trade of Polymers LTDA

Message:
ABS resin for injection in black color, flame retardant (V-0), excellent mechanical and thermal properties.

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
Appearance	Black		
Processing Method	Injection Molding		
Resin ID (ISO 1043)	>ABS<		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13 to 1.15	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	4.5 to 6.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.40 to 0.80	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	40.0	MPa	ASTM D638
Flexural Modulus	2600	MPa	ASTM D790
Flexural Strength	68.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	250	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	70.0	°C	ASTM D648
Flammability	Nominal Value	Test Method	
Flame Rating (3.20 mm)	V-0	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	85.0	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	195 to 230	°C	
Mold Temperature	50.0 to 70.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

