

Pujie CPE-135B

Chlorinated Polyethylene
Zhanhua Pujie Chemical Technology Co.,Ltd

Message:

CPE-135B, Medium molecular weight, Mooney viscosity between 70 and 80, superior mechanical performances, good processibility, quick extrusion and good final product outlook.

General Information		
Features	Workability, good	
	Medium molecular weight	
Uses	Wire and cable applications	
	Pipe	
Processing Method	Extrusion	
Physical	Nominal Value	Unit
Apparent Density	> 0.50	g/cm³
Mooney Viscosity (ML 1+4, 125°C)	70 - 80	MU
Chlorine Content	34.0 - 36.0	wt%
Hardness	Nominal Value	Unit
Durometer Hardness (Shore A)	< 57	
Mechanical	Nominal Value	Unit
Tensile Strength	> 8.00	MPa
Tensile Elongation (Break)	> 700	%
Thermal	Nominal Value	Unit
Heat of Fusion		J/g
Impurities		pcs/50 g
Volatiles		%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT