# THERMOLAST® K TC5HAZ (Series: AD/POM)

## Thermoplastic Elastomer

#### **KRAIBURG TPE**

#### Message:

The AD/POM Series is your material solution for applications with excellent adhesion to POM. The compounds are available in natural and black colors.

Typical applications

Bumpers

Function and design elements

Grommets

Handles (hand tools and power tools etc.)

Seals

Thumb wheels

Material advantages

Easy coloring (compounds in natural colors)

**Excellent adhesion** 

Excellent processing behavior

Insert molding possible

Patented system for TPS and POM

Pleasant surface feel (Soft touch)

Suitable for automotive-interior

**UV** resistance

| General Information                     |                           |       |             |  |  |
|---|---------------------------|-------|-------------|--|--|
| Features                                | Good Adhesion             |       |             |  |  |
|   | Good Processability       |       |             |  |  |
|   | Good UV Resistance        |       |             |  |  |
|   | Soft                      |       |             |  |  |
|   |                           |       |             |  |  |
| Uses                                    | Automotive Interior Parts |       |             |  |  |
|   | Grommets                  |       |             |  |  |
|   | Handles                   |       |             |  |  |
|   | Seals                     |       |             |  |  |
|   |                           |       |             |  |  |
| Appearance                              | Black                     |       |             |  |  |
| Processing Method                       | Injection Molding         |       |             |  |  |
| Physical                                | Nominal Value             | Unit  | Test Method |  |  |
| Density                                 | 1.07                      | g/cm³ | ISO 1183    |  |  |
| Hardness                                | Nominal Value             | Unit  | Test Method |  |  |
| Shore Hardness (Shore A)                | 52                        |       | ISO 7619    |  |  |
| Elastomers                              | Nominal Value             | Unit  | Test Method |  |  |
| Tensile Stress <sup>1</sup> (Yield)     | 3.50                      | МРа   | ISO 37      |  |  |
| Tensile Elongation <sup>2</sup> (Break) | 600                       | %     | ISO 37      |  |  |
| Tear Strength <sup>3</sup>              | 14                        | kN/m  | ISO 34-1    |  |  |
| Compression Set <sup>4</sup>            |                           |       | ISO 815     |  |  |
| 23°C, 72 hr                             | 32                        | %     |             |  |  |

| 70°C, 24 hr        | 78                        | %    |  |
|--------------------|---------------------------|------|--|
| 100°C, 24 hr       | 80                        | %    |  |
| Injection          | Nominal Value             | Unit |  |
| Drying Temperature | 60.0 to 80.0              | °C   |  |
| Drying Time        | 2.0 to 4.0                | hr   |  |
| Rear Temperature   | 180                       | °C   |  |
| Middle Temperature | 210                       | °C   |  |
| Front Temperature  | 240                       | °C   |  |
| Mold Temperature   | 80.0 to 110               | °C   |  |
| Injection Pressure | 20.0 to 100               | MPa  |  |
| Back Pressure      | 2.00 to 10.0              | MPa  |  |
| NOTE               |                           |      |  |
| 1.                 | Type S2, 200 mm/min       |      |  |
| 2.                 | Type S2, 200 mm/min       |      |  |
| 3.                 | Method Bb, Angle (Nicked) |      |  |
| 4.                 | Method A                  |      |  |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

