

Evoprene™ COGEE 637

Styrene Ethylene Butylene Styrene Block Copolymer

AlphaGary

Message:

The Evoprene COGEE range was specially developed to provide materials which will comould or coextrude to engineering thermoplastics (ETPs). This enables, for example, polyamide (nylon) handles or ABS housings to be given a soft touch feel whilst polycarbonate lenses can have gaskets moulded on to provide a weathertight product.

The Evoprene COGEE grades are modified Kraton G based compounds. Many of the characteristics exhibited by the Evoprene G and Evoprene Super G ranges are shown by Evoprene COGEE compounds. However, they do have to be processed quite differently to obtain optimum bond strengths and performance characteristics.

| General Information | | | |
|--------------------------------------|-------------------------------|-------------------|-----------------|
| Features | Good Weather Resistance | | |
| | Ozone Resistant | | |
| Uses | Soft Touch Applications | | |
| Processing Method | Coextrusion | | |
| | Extrusion | | |
| | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 0.930 | g/cm ³ | ISO 2781 |
| Hardness | Nominal Value | Unit | Test Method |
| Shore Hardness (Shore A) | 49 | | ISO 868 |
| Mechanical | Nominal Value | Unit | Test Method |
| Abrasion Resistance | 216 | mm ³ | DIN 53516 |
| Service Temperature | -30 to 60 | °C | |
| Bond Strength | 1.14 | MPa | Internal Method |
| M-S Flow | 0.981 | MPa | Internal Method |
| Ozone Resistance ¹ (35°C) | No Cracks | | ISO 1431-1 |
| UV Rating ² (40°C) | No Visible Cracks or Cracking | | |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Stress | | | ISO 37 |
| 100% Strain | 1.80 | MPa | |
| 300% Strain | 3.50 | MPa | |
| Tensile Stress (Yield) | 4.00 | MPa | ISO 37 |
| Tensile Elongation (Break) | 470 | % | ISO 37 |
| Tear Strength ³ | 22 | kN/m | ISO 34-1 |
| Compression Set | | | ISO 815 |
| 23°C, 72 hr | 43 | % | |
| 70°C, 22 hr | 86 | % | |
| 100°C, 22 hr | 92 | % | |

| Aging | Nominal Value | Unit | Test Method |
|--|-----------------------------|------|-------------|
| Change in Tensile Strength in Air (125°C, 336 hr) | -4.0 | % | ISO 1817 |
| Change in Tensile Strain at Break in Air (125°C, 336 hr) | 2.0 | % | ISO 1817 |
| Change in Shore Hardness in Air (125°C, 336 hr) | -2.0 | | ISO 1817 |
| Injection | Nominal Value | Unit | |
| Drying Temperature | 80.0 | °C | |
| Drying Time | 4.0 to 6.0 | hr | |
| Suggested Max Regrind | 20 | % | |
| Rear Temperature | 250 to 270 | °C | |
| Middle Temperature | 250 to 270 | °C | |
| Front Temperature | 250 to 270 | °C | |
| Nozzle Temperature | 250 to 270 | °C | |
| Processing (Melt) Temp | 280 | °C | |
| Mold Temperature | 30.0 to 60.0 | °C | |
| Injection Rate | Fast | | |
| Vent Depth | 0.020 to 0.050 | mm | |
| NOTE | | | |
| 1. | 100 pphm/200 hrs/20% Strain | | |
| 2. | 350 hrs | | |
| 3. | Method Ba, Angle (Unnicked) | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

