

Topilene® HJ541CP

Polypropylene Homopolymer

Hyosung Corporation

Message:

Characteristics:

Stiffness

Good processability

Impact strength

Applications:

PET bottle cap

General Information	
Features	Good Processability
Uses	Caps
Agency Ratings	DMF 21499
	FDA Unspecified Rating
	USP Class VI

Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	6.5	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	1570	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact			ASTM D256
-10°C	54	J/m	
23°C	110	J/m	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China


WECHAT