

DESOX™ DSC401GW6

Polybutylene Terephthalate

DESCO Co., Ltd.

Message:

Descriptions: DESOX™ DSC401GW6 is one of the brands which made by PBT(Poly Butylene Terephthalate) that filled Glass Fiber 30% and reinforced goods. It provides good electronic property and excellent flame resistance property.

Applications: DESOX™ DSC401GW6 is one of the most-used resin requested for good electrical property and mechanical property parts.

General Information			
UL YellowCard	E251362-466775		
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Features	Good electrical performance		
	Flame retardancy		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.65	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.40 - 0.70	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	122		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	137	MPa	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	9810	MPa	ASTM D790
Flexural Strength	206	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	78	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	220	°C	ASTM D648
1.8 MPa, not annealed	210	°C	ASTM D648
Melting Temperature	222	°C	DSC
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	28	kV/mm	ASTM D149
Arc Resistance	70.0	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	120 - 140	°C	
Drying Time	2.0 - 5.0	hr	
Suggested Max Moisture	< 0.20	%	

Rear Temperature	230 - 245	°C
Middle Temperature	235 - 250	°C
Front Temperature	240 - 260	°C
Nozzle Temperature	240 - 260	°C
Processing (Melt) Temp	240 - 260	°C
Mold Temperature	60.0 - 90.0	°C

Injection instructions

Speed: 40 to 70%Pressure 1st: 30 to 60%Pressure 2nd: 30 to 60Holding Pressure: 10 to 20%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

