

PRL PPX-GP3-(color)-EN

Polyphenylene Ether + PS

Polymer Resources Ltd.

Message:

PRL PPX-GP3-(color)-EN is a polyphenylene ether PS (PPE PS) product. It can be processed by extrusion and is available in North America.

Features include:

ROHS certification

moisture resistance

Heat resistance

Hydrolytic stability

General Information			
Features	Heat resistance, medium		
	Hydrolysis stability		
	General		
	Low or no water absorption		
RoHS Compliance	RoHS compliance		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/11.6 kg)	12 - 18	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	0.50 - 0.70	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	114		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, 3.18mm	46.9	MPa	ASTM D638
Fracture, 3.18mm	43.4	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield, 3.18mm	3.0	%	ASTM D638
Fracture, 3.18mm	25	%	ASTM D638
Flexural Modulus (3.18 mm)	2210	MPa	ASTM D790
Flexural Strength (3.18 mm)	72.4	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	15	kJ/m²	ISO 179/1
Notched Izod Impact			
-40°C, 3.18 mm	130	J/m	ASTM D256
23°C, 3.18 mm	210	J/m	ASTM D256
-30°C	4.2	kJ/m²	ISO 180/1A

23°C	15	kJ/m ²	ISO 180/1A
Dart Drop Impact (3.18 mm)	16.9	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, 3.18mm	113	°C	ASTM D648
1.8 MPa, unannealed, 3.18mm	107	°C	ASTM D648
Vicat Softening Temperature	127	°C	ASTM D1525 ¹
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Extrusion	Nominal Value	Unit	
Drying Temperature	104 - 110	°C	
Drying Time	3.0 - 4.0	hr	
Cylinder Zone 1 Temp.	216	°C	
Cylinder Zone 2 Temp.	238	°C	
Cylinder Zone 3 Temp.	249	°C	
Melt Temperature	243 - 271	°C	
Die Temperature	249	°C	
Extrusion instructions			
Do not exceed 8 hour drying time.			
NOTE			
1.	标准 B (120°C/h), 载荷2 (50N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT