Geon[™] Vinyl Fittings M1030

Rigid Polyvinyl Chloride

PolyOne Corporation

Message:

Geon[™] Vinyl Fittings M1030 is a Rigid Polyvinyl Chloride product. It can be processed by injection molding and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Applications of Geon[™] Vinyl Fittings M1030 include plumbing/piping/potable water and engineering/industrial parts.

| General Information | | | |
|---|--------------------|-------|-------------|
| Features | Medium Flow | | |
| Uses | Fittings | | |
| Agency Ratings | NSF 14 | | |
| | NSF 61 | | |
| | NSF Type I 3 | | |
| | | | |
| Forms | Pellets | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.41 | g/cm³ | ASTM D792 |
| Spiral Flow | 71.1 | cm | |
| Molding Shrinkage - Flow | 0.20 to 0.50 | % | ASTM D955 |
| PVC Cell Classification | 12454 | | ASTM D1784 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore D) | 74 | | ASTM D2240 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus ¹ | 3030 | MPa | ASTM D638 |
| Tensile Strength ² (Yield) | 52.4 | MPa | ASTM D638 |
| Flexural Modulus | 3030 | MPa | ASTM D790 |
| Flexural Strength | 87.6 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (23°C, 3.18 mm, Injection Molded) | 44 | J/m | ASTM D256A |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (1.8 MPa, Annealed, 3.18 mm) | 70.0 | °C | ASTM D648 |
| Injection | Nominal Value | Unit | |
| Processing (Melt) Temp | 199 to 210 | °C | |
| NOTE | | | |
| 1. | Type I, 5.1 mm/min | | |
| 2. | Type I, 5.1 mm/min | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

