

MAJORIS DG308X

Polypropylene

AD majoris

Message:

MAJORIS DG308X is a high performance reinforced polypropylene compound intended for injection moulding.

The product is available in natural, but other colours can be provided on request.

MAJORIS DG308X has been developed especially for demanding applications in various engineering sectors.

MAJORIS DG308X has high rigidity and impact strength, good dimensional stability, very good stiffness and good creep resistancy also at high temperatures.

APPLICATIONS

Product requiring very high overall mechanical performance such as:

Electrical tool and appliance components

Under the bonnet parts

Miscellaneous technical items

| General Information | | | |
|---|------------------------------------|-------------------|-----------------|
| Features | Good dimensional stability | | |
| | Rigidity, high | | |
| | Rigidity, high | | |
| | Impact resistance, high | | |
| | Recyclable materials | | |
| | Good creep resistance | | |
| Uses | Electrical/Electronic Applications | | |
| | Power/other tools | | |
| | Home appliance components | | |
| | Parts under the hood of a car | | |
| Appearance | Available colors | | |
| | Natural color | | |
| Forms | Particle | | |
| Processing Method | Injection molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 1.18 | g/cm ³ | ISO 1183 |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) | 4.5 | g/10 min | ISO 1133 |
| Molding Shrinkage | | | Internal method |
| Vertical flow direction: 2.00mm | 1.0 | % | Internal method |
| Flow direction: 2.00mm | 0.20 | % | Internal method |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus | 9600 | MPa | ISO 527-2/1 |
| Tensile Stress (Yield) | 122 | MPa | ISO 527-2/50 |

| | | | |
|--|---------------|-------------------|--------------|
| Tensile Strain (Break) | 2.7 | % | ISO 527-2/50 |
| Flexural Modulus ¹ | 8000 | MPa | ISO 178 |
| Flexural Stress | 190 | MPa | ISO 178 |
| Impact | Nominal Value | Unit | Test Method |
| Charpy Notched Impact Strength (23°C) | 14 | kJ/m ² | ISO 179/1eA |
| Charpy Unnotched Impact Strength (23°C) | 62 | kJ/m ² | ISO 179/1eU |
| Thermal | Nominal Value | Unit | Test Method |
| Heat Deflection Temperature | | | |
| 0.45 MPa, not annealed | 169 | °C | ISO 75-2/B |
| 1.8 MPa, not annealed | 162 | °C | ISO 75-2/A |
| Flammability | Nominal Value | | Test Method |
| Flame Rating | HB | | UL 94 |
| Injection | Nominal Value | Unit | |
| Processing (Melt) Temp | 230 - 270 | °C | |
| Mold Temperature | 30.0 - 60.0 | °C | |
| Injection Rate | Moderate | | |
| Holding Pressure | 30.0 - 60.0 | MPa | |
| Injection instructions | | | |
| Screw speed: Low to mediumBack pressure: Low to medium | | | |
| NOTE | | | |
| 1. | 2.0 mm/min | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT