

Sumikon® PM-3050

Phenolic

SBHPP

Message:

SUMIKON® PM-3050 (Type J Black) is Glass fiber, Inorganic filler and Organic fiber filled novolac resin molding compound with good mechanical property.

General Information	
Filler / Reinforcement	Glass fiber reinforced material Inorganic filler Organic filler
RoHS Compliance	RoHS compliance
Appearance	Black
Forms	Powder Particles
Processing Method	Resin transfer molding Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.65	g/cm ³	JIS K6911
Molding Shrinkage - Flow	0.26	%	JIS K6911
Water Absorption (Equilibrium)	0.12	%	JIS K6911
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	117	MPa	JIS K6911
Flexural Modulus	12900	MPa	JIS K6911
Flexural Strength	197	MPa	JIS K6911
Compressive Strength	251	MPa	JIS K6911
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	5.2	kJ/m ²	JIS K6911
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	205	°C	JIS K6911
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength ¹	16	kV/mm	JIS K6911
Insulation Resistance			JIS K6911
-- ²	4.0E+11	ohms	JIS K6911
-- ³	5.0E+10	ohms	JIS K6911
NOTE			
1.	Method B (step by step)		

- | | |
|----|---------------|
| 2. | As molded |
| 3. | After boiling |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

