Sanren Q200 (Premium-grade)

Low Density Polyethylene

SINOPEC Shanghai Petrochemical Co. Ltd.

Message:

Features

General Information

The oblate pellet product is colourless with excellent chemical stability. Under the normal conditions, the product is acid resistant, alkali resistant, and salt resistant. It possesses certain mechanical properties. good dielectric characteristics and excellent light transmittance.

Scope of Application: Light-duty film, Laminated film and small size injection mouldings.

High Light Transmission

	Low density		
	Homopolymer		
	Good electrical performance		
	alkali resistance		
	acid resistance		
Uses	Films		
	Laminate		
Appearance	Colorless		
Forms	Particle		
Processing Method	Blow molding		
	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.922	g/cm³	Internal method
Melt Mass-Flow Rate (MFR) (190°C/2.16	46.04	40	
kg)	1.6 - 2.4	g/10 min	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	> 11.0	MPa	Internal method
Tensile Elongation (Break)	> 550	%	Internal method
Optical	Nominal Value	Unit	Test Method
Haze	< 9.0	%	Internal method
Additional Information	Nominal Value	Unit	
Blocking	0.0260	МРа	
Fish Eye			
0.300 to 2.00mm		pcs/1200 cm ²	
Linking: 0.500 to 2.00mm		pcs/20 cm ²	
Hue			

Streaks

Cleanliness: <10 pieces/kg

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

В

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

