

RTP ESD A 2800-85A

Thermoplastic Polyolefin Elastomer

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.
Static Dissipative - 85 Shore A

General Information			
Features	Electrostatic discharge protection		
	Static conduction		
RoHS Compliance	Contact manufacturer		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.01	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	1.6 - 2.0	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	85		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	9.65	MPa	ASTM D412
Tensile Elongation (Yield)	500	%	ASTM D412
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	5.0E+5	ohms	ASTM D257
Volume Resistivity	5.0E+4	ohms · cm	ASTM D257
Additional Information			
Dew Point: 0°FMoisture Content: 0.03%Static Decay, FTMS101C, 4046.1, MIL-PRF-81705D, 50V to 5kV, 12%RH: 500%Volume Resistivity, ASTM D257: 1000 to 9900000000 ohm-cm			
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	182 - 210	°C	
Mold Temperature	15.6 - 65.6	°C	
Injection Pressure	82.7 - 124	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

