

MARCOBLEND R3

Polycarbonate

POLY GIN

Message:

MARCOBLEND R3 is an ignition resistant and glass fiber reinforced polycarbonate resin. The resin is Halogen free and compliance with TCO and RoHS certification. The unique characters include superior processability, good stiffness, and excellent dimension stability and suitable for use in TFT LCD frame and internal structure parts.

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
	Good Dimensional Stability		
	Good Processability		
	Good Stiffness		
	Halogen Free		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.25	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	16	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.30 to 0.50	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	70.0	MPa	ASTM D638
Flexural Modulus	3380	MPa	ASTM D790
Flexural Strength	110	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	120	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	145	°C	
1.8 MPa, Unannealed	126	°C	
CLTE			ASTM D696
Flow	4.0E-5	cm/cm/°C	
Transverse	6.5E-5	cm/cm/°C	
Flammability	Nominal Value	Test Method	
Flame Rating	V-0	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	3.0 to 4.0	hr	

Rear Temperature	260 to 265	°C
Middle Temperature	265 to 270	°C
Front Temperature	270 to 275	°C
Nozzle Temperature	275 to 280	°C
Mold Temperature	80.0 to 120	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT