

# SABIC® LDPE HP2022N

Low Density Polyethylene

SABIC Americas, Inc.

## Message:

### Product Description

HP2022 series resins are Low Density Polyethylene grades suitable for general purpose packaging. They exhibit better draw down, good opticals and mechanical properties.

### Typical Applications

Thin shrink film, lamination film, produce bags, textile packaging, soft goods packaging, general purpose bags with good optics and t-shirts carrier bags.  
HP2022N: No Slip & No Antiblock

General Information			
Features	Low density		
	Optical		
	Good stripping		
	Compliance of Food Exposure		
Uses	Packaging		
	Films		
	Laminate		
	Bags		
	Shrinkable film		
Forms	Particle		
Processing Method	Blow film		
Physical	Nominal Value	Unit	Test Method
Density	0.922	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/21.6 kg)	0.75	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	30	µm	
secant modulus			ASTM D882
1% secant, MD: 30 µm, blown film	160	MPa	ASTM D882
1% secant, TD: 30 µm, blown film	180	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Yield, 30 µm, blown film	8.00	MPa	ASTM D882
TD: Yield, 30 µm, blown film	7.00	MPa	ASTM D882
MD: Broken, 30 µm, blown film	21.0	MPa	ASTM D882
TD: Broken, 30 µm, blown film	18.0	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Broken, 30 µm, blown film	290	%	ASTM D882
TD: Broken, 30 µm, blown film	570	%	ASTM D882

Dart Drop Impact (30 μm, Blown Film)	80	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD: 30 μm, blown film	180	g	ASTM D1922
TD: 30 μm, blown film	150	g	ASTM D1922
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	92.0	°C	ASTM D1525
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 30.0 μm, Blown Film)	80		ASTM D2457
Haze (30.0 μm, Blown Film)	7.0	%	ASTM D1003
Additional Information	Nominal Value		
Blow-up Ratio	2.00 - 3.00		
Properties have been measured by producing 30 μ film with 2.5 BUR using 100% HP2022N.			
Extrusion	Nominal Value	Unit	
Melt Temperature	160 - 180	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

