

Adell Polyamide AF-10-667B

Polyamide 66

Adell Plastics, Inc.

Message:

Adell Polyamide AF-10-667B is a Polyamide 66 (Nylon 66) material. It is available in North America. Primary attribute of Adell Polyamide AF-10-667B: Flame Retardant.

General Information			
UL YellowCard	E44974-235686		
Features	Flame Retardant		
Appearance	Natural Color		
	White		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.49	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.50 to 0.80	%	ASTM D955
Water Absorption (24 hr)	0.80	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	75.8	MPa	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	5170	MPa	ASTM D790
Flexural Strength (Yield)	110	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	27	J/m	ASTM D256
Tensile Impact Strength	73.6	kJ/m ²	ASTM D1822
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	232	°C	
1.8 MPa, Unannealed	149	°C	
Melting Temperature	249 to 260	°C	
RTI Elec (0.710 mm)	130	°C	UL 746
RTI Imp			UL 746
0.710 mm	75.0	°C	
1.47 mm	80.0	°C	
RTI Str			UL 746
0.710 mm	120	°C	
1.47 mm	130	°C	
Electrical	Nominal Value	Unit	Test Method
Arc Resistance (3.05 mm)	60.0	sec	ASTM D495

Comparative Tracking Index (CTI) (3.05 mm)	138	V	UL 746
High Amp Arc Ignition (HAI)			UL 746
0.710 mm	45.0		
3.05 mm	90.0		
High Voltage Arc Tracking Rate (HVTR)			UL 746
0.710 mm	115	mm/min	
3.05 mm	17.5	mm/min	
Hot-wire Ignition (HWI)			UL 746
0.710 mm	45	sec	
1.47 mm	90	sec	
3.05 mm	120	sec	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

