

SD POLYCA™ CR3241

Polycarbonate + PET

Sumika Styron Polycarbonate Limited

Message:

SD POLYCA CR series are PC/Polyester alloy grades. These products have improved chemical resistant property in addition to high impact property and heat resistant property of polycarbonate resin.

General Information			
Features	Impact resistance, high		
	Good chemical resistance		
	Heat resistance, high		
Uses	Automotive exterior parts		
Appearance	Opacity		
Part Marking Code	>PC+PET		
Physical	Nominal Value	Unit	Test Method
Density	1.21	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (280°C/1.2 kg)	5.00	cm ³ /10min	ISO 1133
Molding Shrinkage			ASTM D955
Flow	0.60 - 0.80	%	ASTM D955
Transverse flow	0.60 - 0.80	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.20	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2200	MPa	ISO 527-2
Tensile Strength			
--	61.0	MPa	ASTM D638
--	60.0	MPa	ISO 527-2
Tensile Elongation			
Fracture	130	%	ASTM D638
Fracture	100	%	ISO 527-2
Flexural Modulus			
--	2160	MPa	ASTM D790
--	2200	MPa	ISO 178
Flexural Strength			
--	88.0	MPa	ASTM D790
--	85.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	65	kJ/m ²	ISO 179

Notched Izod Impact (23°C)	780	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, not annealed	138	°C	ASTM D648
1.8 MPa, not annealed	120	°C	ASTM D648
1.8 MPa, not annealed	115	°C	ISO 75-2/A
Linear thermal expansion coefficient			ASTM D696
Flow	7.0E-5	cm/cm/°C	ASTM D696
Lateral	7.0E-5	cm/cm/°C	ASTM D696

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

