Flexirene® MS 40 U

Linear Low Density Polyethylene

Versalis S.p.A.

Message:

Flexirene MS 40 U is a linear low density polyethylene (LLDPE) with antioxidants, suitable for injection moulding application. Parts made by Flexirene MS 40 U are characterised by a good balance between impact resistance and rigidity. Main Application

Flexirene MS 40 U is recommended for the production of large sized articles, houseware and toys. Flexirene MS 40 U is characterized by a high flowability which make it ideal for masterbatches preparation for LDPE and LLDPE.

General Information					
Additive	Antioxidant				
Features	Antioxidant				
	Food Contact Acceptable				
	Good Impact Resistance				
	High Flow				
	Low Density				
	Medium Rigidity				
Uses	Household Goods				
	Masterbatch				
	Toys				
Agency Ratings	EU Food Contact, Unspecified Rating				
Forms	Pellets				
Processing Method	Injection Molding				
Physical	Nominal Value	Unit	Test Method		
Density	0.930	g/cm³	ISO 1183		
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	27	g/10 min	ISO 1133		
Hardness	Nominal Value	Unit	Test Method		
Shore Hardness (Shore D, Injection Molded)	52		ISO 868		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Stress			ISO 527-2		
Yield, Injection Molded	11.0	MPa			
Break, Injection Molded	12.0	MPa			
Tensile Strain (Break, Injection Molded)	> 500	%	ISO 527-2		
Flexural Modulus (Injection Molded)	300	MPa	ISO 178		
Thermal	Nominal Value	Unit	Test Method		
Brittleness Temperature	< -70.0	°C	ASTM D746		
Vicat Softening Temperature	103	°C	ISO 306/A		

Melting Temperature	121	°C	Internal Method
Injection	Nominal Value	Unit	
Rear Temperature	160 to 210	°C	
Middle Temperature	160 to 210	°C	
Front Temperature	160 to 210	°C	
Mold Temperature	10.0 to 40.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

