

Hax™ HFX 509

Polyolefin
Fainplast Compounds S.r.l

Message:
This is a range of polyolefin based HFFR silane grafted compounds that are cross-linkable by heat and moisture and by previous addition of a suitable catalyst (SIOPLAS method). This solution is suitable for the production of crosslinked insulation or sheathing without the use of specific curing equipment.
Application: Insulation solar cables

General Information			
Additive	Flame Retardant		
Features	Crosslinkable		
	Flame Retardant		
	Halogen Free		
Uses	Insulation		
	Solar Panels		
	Wire & Cable Applications		
Wire Types	M2		
Agency Ratings	CEI 20-91 M21		
	EN 50363-0		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.49	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (150°C/21.6 kg)	4.0	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 15 sec)	49		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	14.0	MPa	ISO 527-2
Tensile Strain (Break)	210	%	ISO 527-2
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (20°C)	4.0E+15	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	32	%	ISO 4589-2

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

