

LUVOCOM® 1105-7106 VP

Polyetheretherketone
Lehmann & Voss & Co.

Message:

LUVOCOM®1105-7106 VP is a polyetheretherketone (PEEK) material, and the filler is carbon fiber reinforced material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific.

LUVOCOM®The main characteristics of 1105-7106 VP are:

flame retardant/rated flame

Flame Retardant

Good dimensional stability

chemical resistance

Wear-resistant

Typical application areas include:

engineering/industrial accessories

textile/fiber

Aerospace

Automotive Industry

medical/health care

| General Information | | | |
|------------------------|----------------------------------|------|-------------|
| Filler / Reinforcement | Carbon fiber reinforced material | | |
| Additive | PTFE lubricant | | |
| Features | Good dimensional stability | | |
| | Low friction coefficient | | |
| | Good chemical resistance | | |
| | Good wear resistance | | |
| | Heat resistance, high | | |
| | Lubrication | | |
| | Hydrolysis stability | | |
| | Self-lubricating | | |
| | Flame retardancy | | |
| Uses | Pump parts | | |
| | Bushing | | |
| | Gear | | |
| | Textile applications | | |
| | Engineering accessories | | |
| | Aerospace applications | | |
| | Application in Automobile Field | | |
| | Medical/nursing supplies | | |
| | Bearing | | |
| Appearance | Natural color | | |
| Physical | Nominal Value | Unit | Test Method |

| | | | |
|---|----------------------|------------------------|--------------------|
| Density | 1.45 | g/cm ³ | ISO 1183 |
| Melt Volume-Flow Rate (MVR) (380°C/10.0 kg) | 11.0 | cm ³ /10min | ISO 1133 |
| Molding Shrinkage | 0.30 - 0.60 | % | DIN 16901 |
| Water Absorption (23°C, 24 hr) | < 0.10 | % | |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus | 10000 | MPa | ISO 527-2 |
| Tensile Stress (Break) | 100 | MPa | ISO 527-2 |
| Tensile Strain (Yield) | 3.2 | % | ISO 527-2 |
| Flexural Modulus | 9000 | MPa | ISO 178 |
| Flexural Stress | 145 | MPa | ISO 178 |
| Coefficient of Friction | | | |
| Dynamic | 0.12 | | |
| Static | 0.11 | | |
| Flexural Strain at Flexural Strength | 4.2 | % | ISO 178 |
| Maximum operating temperature-Short Term | 280 | °C | |
| Insulation Resistance | | ohms | IEC 60167 |
| Impact | Nominal Value | Unit | Test Method |
| Charpy Notched Impact Strength (23°C) | 7.0 | kJ/m ² | ISO 179/1eA |
| Charpy Unnotched Impact Strength (23°C) | 30 | kJ/m ² | ISO 179/1eU |
| Thermal | Nominal Value | Unit | Test Method |
| Heat Deflection Temperature (1.8 MPa, Unannealed) | 260 | °C | ISO 75-2/A |
| Continuous Use Temperature | 250 | °C | UL 746B |
| CLTE - Flow | 4.0E-5 | cm/cm/°C | DIN 53752 |
| Electrical | Nominal Value | Unit | Test Method |
| Surface Resistivity | < 1.0E+9 | ohms | IEC 60093 |
| Flammability | Nominal Value | Unit | Test Method |
| Flame Rating ¹ | V-0 | | UL 94 |
| Injection | Nominal Value | Unit | |
| Drying Temperature | | | |
| Hot air dryer, A | 150 | °C | |
| Hot air dryer, B | 120 | °C | |
| Drying Time | | | |
| Hot air dryer, A | 3.0 - 6.0 | hr | |
| Hot air dryer, B | 6.0 - 8.0 | hr | |
| Suggested Max Moisture | 0.050 | % | |
| Rear Temperature | 360 - 370 | °C | |
| Middle Temperature | 380 - 390 | °C | |
| Front Temperature | 390 - 400 | °C | |
| Nozzle Temperature | 360 - 380 | °C | |
| Processing (Melt) Temp | 390 | °C | |

| | | |
|---|-----------|----|
| Mold Temperature | 170 - 190 | °C |
| Injection instructions | | |
| <p>General</p> <p>In general LUVOCOM® can be processed on conventional injection moulding machines while observing the usual technical guidelines. Any added fibrous materials or fillers may have an abrasive effect. In this case the cylinder and screw should be protected against wear as is usual in the processing of reinforced thermoplastic materials.</p> <p>Lengthy dwell times for the melts in the cylinder should be avoided.</p> <p>Lower the temperatures during interruptions!</p> <p>Predrying (optional)</p> <p>It is advisable to predry the granulate with a suitable dryer immediately before processing.</p> <p>The granulate may absorb moisture from the air.</p> <p>Delivery Form & Storage</p> <p>Unless indicated otherwise, the material is delivered as 3mm-long pellets in sealed bags on pallets.</p> <p>Preferably storage should be effected in dry and normally temperatured rooms</p> <p>Additional Information</p> <p>During processing, the moisture content should not exceed 0.05%. To avoid internal stresses, a medium to high injection rate should be used. An increase in tool temperature may be helpful. Post-crystallization may lead to warpage at elevated operating temperatures. This can be counteracted by suitable heat treatment.</p> <p>The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application.</p> <p>High-temperature polymers place increased demands on the tool steels employed.</p> <p>Please contact us for further information.</p> | | |

| | | |
|------|-----------------------|--|
| NOTE | | |
| 1. | Not recognized by UL. | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT