

SEETEC PP H1500

Polypropylene Homopolymer

LG Chem Ltd.

Message:

Application

Housewares, Toys

Description

SÉETEC H1500 is polypropylene homopolymer suitable for injection molding applications. SÉETEC H1500 exhibits a high flow property combined with a good mechanical property balance.

General Information			
UL YellowCard	E140737-223133		
Features	High Flow		
Uses	Toys		
Agency Ratings	FDA 21 CFR 177.1520		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	105		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	34.0	MPa	ASTM D638
Tensile Elongation ² (Break)	> 500	%	ASTM D638
Flexural Modulus ³	1600	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	29	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	110	°C	ASTM D648
Vicat Softening Temperature	151	°C	ASTM D1525 ⁴
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	28 mm/min		
4.	Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

