

Bapolene® PP5062

Polypropylene Copolymer

Bamberger Polymers, Inc.

Message:

Polypropylene injection impact copolymer with excellent color and processability. This resin offers a superior balance of stiffness and impact strength. This product meets the FDA requirements of 21CFR 177.1520.

General Information			
Features	Copolymer		
	Good Colorability		
	Good Impact Resistance		
	Good Processability		
	Good Stiffness		
Uses	Appliances		
	Battery Cases		
	Consumer Applications		
	Furniture		
	Household Goods		
	Toys		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.905	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	83		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	27.6	MPa	ASTM D638
Tensile Elongation ²			ASTM D638
Yield	14	%	
Break	> 200	%	
Flexural Modulus - 1% Secant	1240	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	130	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	103	°C	ASTM D648

NOTE

- | | |
|----|-----------|
| 1. | 51 mm/min |
| 2. | 51 mm/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

