

# KW Plastics KW 1250G

Polypropylene Copolymer

KW Plastics

Message:

Copolymer Polypropylene Post-Consumer Resin  
Injection Molding  
CHARACTERISTICS  
Good impact resistance. Available as mixed color and pre-colored black.

General Information			
Recycled Content	Yes		
Features	Copolymer		
	Good Impact Resistance		
Appearance	Black		
	Colors Available		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.910	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR)	11	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	22.8	MPa	ASTM D638
Tensile Elongation (Yield)	11	%	ASTM D638
Flexural Modulus	896	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	110	J/m	ASTM D256

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT