

Jam HD7255*

High Density Polyethylene
Jam Petrochemical Company

Message:

For thick walled, highly stressed transport containers. e.g refuse bins and fish crates.

- Features
High impace streng
low warpage
Applications
Injection moulding

General Information			
Additive	Antioxidation		
	Lubricant		
Features	Low warpage		
	Antioxidation		
	Impact resistance, high		
	Lubrication		
Uses	Container		
	Loading box		
Processing Method		Injection molding	
Physical	Nominal Value	Unit	Test Method
Density	0.954	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			ISO 1133
190°C/2.16 kg	4.0	g/10 min	ISO 1133
190°C/5.0 kg	11	g/10 min	ISO 1133
Flow Rate Ratio - 5/2.16	2.80		
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C, Compression Molded)	> 5.0	kJ/m ²	ISO 179/1eA

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

